



ETERNAL MATERIALS CO., LTD.

ETERPEARL XJ2008

INCI NAME Dimethicone / Vinyl Dimethicone Crosspolymer (and) Silica

TECHNICAL DATA

Description

ETERPEARL XJ2008 is a Silicone rubber powder, The product Widely used in all kinds of cosmetics and personal care. Unique organic and inorganic composite molecular structure and geometric shape, With it outstanding smooth and light scattering effect, Making makeup look more natural and skin feeling more fresh and smooth.

Key Features

- Improve scatter reflection, Making makeup look more natural
- Small friction coefficient, Making skin feeling more fresh and smooth.
- Excellent spreadability, Can even coated with the skin surface
- Enhanced Skin's smoothness and softness feeling
- Excellent water repellency, Making makeup More durable

Application

Color cosmetic and skin care products, Such as Pressed powder, Foundations, BB Cream, Lipstick, Body lotion, Liquid foundations Eyelash cream , etc


Specifications

Appearance	White powder
Odor	Odorless
Non-Volatile Matter	>97%
Average particle size	1-10 μm
Heavy Metals	<20 ppm
As	<2 ppm

Physical properties

Oil Absorption(Linseed oil)	75ml/100 g
-----------------------------	------------

Shape (SEM, Magnification: 2000 $\times$)



Packaging

- kraftpaper pail, net weight 10 kg / 20 kg

Storage

1. Avoid direct sunlight, and store in a cool and dry place
2. Keep container closed

Cautions

1. Wearing mask, glasses and gloves when operating , Avoid contact with skin, eyes, or clothing , wash with plenty of soap water especially the eyes if contacted
2. This product is Non-dangerous goods in FIRE CODE , But the place full of dust has the potential to cause dust explosion. It is strictly prohibited to contact fire
3. For more information, please refer to the 【MSDS】 .

ETERNAL MATERIALS CO., LTD.

307 petrochemical 9th Road, Gaolan port Economic Zone, Zhuhai, Guangdong ,China Tel: 86-0756-3985888 FAX: 86-0756-3985111
578, CHIEN-KUNG RD. KAOHSIUNG, TAIWAN, 807. R.O.C. www.eternal.com.tw. Tel: 886-7-3838181 FAX: 886-7-3833355

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty negligence or otherwise is limited to the purchase price of the material.